



LUBRICANTS



# Product Data Sheet

## Gulfsyn EP Gear Lubricants

### *Synthetic Extreme Pressure (EP) Gear Oil*

Premium synthetic extreme pressure (EP) gear oils designed to provide extra protection and very long service life in highly loaded gear boxes that may be operated over a wide temperature range. They are designed to protect heavily loaded gears and bearings in extreme pressure service that includes sustained high temperatures. They are capable of much longer drain interval service than conventional industrial gear oils and usually eliminate the need for seasonal changes due to their very good low temperature flow characteristics.

### Features and Benefits

- Excellent EP protection
- Extremely low pour points
- Excellent rust and corrosion protection
- Excellent oxidation resistance and thermal stability
- Excellent lubrication flow characteristics over a wide temperature range

### Applications

Recommended for heavily loaded industrial gear boxes where excellent lubrication is required over a wide range of operating temperatures and extended drain intervals are essential. Applications include the following in the appropriate viscosity grade:

- DIN 51517-3
- US Steel 224
- ISO 12925-1 CKC/CKD
- GM LS-2
- Cincinnati Machine (Gear C Series)
- AGMA 9005-E02 EP



1-800-566-4853



East Greenbush, NY



[www.nu-tierbrands.com](http://www.nu-tierbrands.com)





LUBRICANTS

# Product Data Sheet

## Typical Properties

ISO Viscosity Grade	Test Method	68	100	150	220
Product Code		343901	343902	343903	343904
AGMA Number		2EP	3EP	4EP	5EP
Viscosity, cSt @ 40°C	ASTM D-445	67	100	145	220
Viscosity, cSt @ 100°C	ASTM D-445	11.6	14.0	19.0	25.5
Viscosity Index	ASTM D-2270	169	142	149	147
Flash Point, COC, °F (°C)	ASTM D-92	473(245)	473(245)	482(250)	482(250)
Pour Point, °F (°C)	ASTM D-97	-44(-42)	-40(-40)	-40(-40)	-40(-40)
Timken OK Load, lb.	ASTM D-2782	70	65	65	75
4-Ball EP Weld, kg	ASTM D-2783	250	250	315	315
4-Ball Wear, mm	ASTM D-2266	0.4	0.4	0.4	0.4
FZG Gear Test, Stages	FZG	12+	12+	12+	12+
Rust Test	ASTM D-665A	Pass	Pass	Pass	Pass
Copper Strip Corrosion	ASTM D-130	1a	1a	1a	1a

ISO Viscosity Grade	Test Method	320	460	680	1000
Product Code		343905	343906	343907	343908
AGMA Number		6EP	7EP	8EP	8EP
Viscosity, cSt @ 40°C	ASTM D-445	340	440	670	1000
Viscosity, cSt @ 100°C	ASTM D-445	35.0	43.0	60.5	73
Viscosity Index	ASTM D-2270	147	150	158	144
Flash Point, COC, °F (°C)	ASTM D-92	482(250)	482(250)	482(250)	482(250)
Pour Point, °F (°C)	ASTM D-97	-40(-40)	-35(-37)	-30(-34)	0 (-18)
Timken OK Load, lb.	ASTM D-2782	75	75	75	75
4-Ball EP Weld, kg	ASTM D-2783	315	315	315	315
4-Ball Wear, mm	ASTM D-2266	0.4	0.35	0.35	0.35
FZG Gear Test, Stages	FZG	12+	12+	12+	12+
Rust Test	ASTM D-665A	Pass	Pass	Pass	Pass
Copper Strip Corrosion	ASTM D-130	1a	1a	1a	1b

These properties are typical of current production, minor variations are to be expected in normal manufacturing.

Rev. 05/21



1-800-566-4853



East Greenbush, NY



www.nu-tierbrands.com

