

---

**PRODUCT  
INFORMATION****NOX-RUST® X-121 BLACK****Rust-Proofing Underbody Wax****Description**

NOX-RUST® X-121 BLACK is a thixotropic wax-gel rustproofing compound designed to provide a long-term protective film for automotive primed and

unprimed steel. NOX-RUST® X-121 BLACK will dry to a firm wax-like film that will repel water, self-heal, and remain flexible at low temperatures.

---

**Application**

NOX-RUST® X-121 BLACK can be easily applied using low pressure airless equipment. For best results, Daubert recommends the following conditions:

Pump:	10:1 to 40:1
Hose:	3/8 ID Minimum
Air Pressure:	500-800 Lbs. at Tip
Tip:	Roto-Clean Type, Tungsten Carbide 3-17 to 3-25
Coverage Rate:	140 to 170 Sq.Ft./Gal.

NOX-RUST® X-121 BLACK has a thixotropic wax-gel that requires moderate stirring before use. Continuous agitation and thinning is not generally required. If product thickens due to solvent loss, add aliphatic mineral spirits. The recommended film thickness for NOX-RUST® X-121 BLACK is 10-12 mils wet (5-6 mils dry). The coating will dry to touch in four hours and be tack-free overnight.

**NOTE: For easy bodyshop or field application, NOX-RUST® X-121 BLACK is available in aerosol spray cans (12 cans per case, part no. 1786060).**

**Physical Properties****Typical Values**

Appearance:	Black Thixotropic Liquid
Odor:	Mild Petroleum Odor
Film:	Firm, Wax-Like Film
Specific Gravity:	1.0 ± .03
Weight per Gallon:	8.4 ± 0.2 lbs/gal
Non-Volatile by Weight	68 ± 3%
Non-Volatile by Volume:	57 ± 3%
VOC:	2.8 LBS VOC/Gal
Viscosity @ 77°F (25°C Spindle #6 @ 10 RPM)	6,000-20,000 CPS
Solvent:	Mineral Spirits, Rule 66 Type
Weight Per Gallon of Solvent:	6.5 lbs/gal
Flash Point:	105°F
Storage Stability:	1 Year Minimum

## Performance Properties

Salt Spray (5% ASTM-B-117):	2000 Hrs. (Min.)
Q.U.V. (ASTM G-53-84):	2000 Hrs. (Min.)
Humidity (ASTM-D-1748):	4000 Hrs. (Min.)
Low Temperatures Flexibility (MIL-C-0083933-A MR):	-20°F
High Temperature Flow (MIL-C-0083933-A MR)	350°F
Fire Resistance (MIL-C-0083933-A MR)	Pass – Will not support combustion.
Water Displacement (MIL-C-0083933-A MR)	Pass – Will displace condensed water off steel.
G.M. Corrosion Cycles (FBTM 54-12 #C):	Pass – 30 Cycles

## Removal

The wet and dry films of NOX-RUST® X-121 BLACK can be removed using mineral spirits or kerosene.

September 20, 2011:co

**CAUTION:** The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

**WARRANTY:** Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

**DAUBERT**  
CHEMICAL COMPANY, INC.

PAGE 2 OF 2

4700 South Central Avenue ■ Chicago, IL 60638 ■ 1-800-688-0459 ■ or 708-496-7350 ■ Fax: 708-496-7367

Visit our web site at [www.daubert.com](http://www.daubert.com) ■ Our e-mail is [dauchem@daubert.com](mailto:dauchem@daubert.com)

