



SUNOCO SUNVIS 600 ASHLESS AW INHERENTLY BIODEGRADABLE HYDRAULIC OILS

OVERVIEW

SUNOCO SUNVIS 600 ASHLESS HYDRAULIC OILS are non-toxic, inherently biodegradable, zinc-free, anti-wear hydraulic oils developed to meet the requirements of high-pressure hydraulic systems operating in areas of environmental concern. These high-quality ashless, oils are non-toxic to fish and other aquatic life and are designed for use in vane, rotary, and geared pumps, and compressors, as well as circulating systems and machine tools.

FEATURES & BENEFITS

SUNOCO SUNVIS 600 ASHLESS HYDRAULIC OILS are characterized by their outstanding ability to prevent wear, rust, oxidation, foam, air and water entrainment and provide excellent thermal stability all while being non-toxic and biodegradable. **SUNOCO SUNVIS 600 ASHLESS HYDRAULIC OILS** are recommended for applications where the use of lubricants containing toxic heavy metals is restricted because of soil or water contamination concerns.

APPLICATIONS

SUNOCO SUNVIS 600 ASHLESS HYDRAULIC OILS are designed primarily for use in hydraulic systems located near environmentally sensitive areas such as national parks, wildlife refuges and ski resorts, but can be used in any hydraulic system where quality and environmental responsibility is of concern or where a zinc-free fluid is specified by the OEM.

SPECIFICATIONS

Hitachi Advanced Hydraulic Oil • DIN 51524 Part 3, Anti-wear Hydraulic Oils (Type HVLP) • AFNOR NFE 48-603 (Type HV) • ISO 11158:1997 (Type HV) • Poclairn • Hitachi • Cincinnati Lamb • Eaton-Vickers I-286, M-2950-S, 35VQ25A • Parker-Hannifin (Denison) HF-0, HF-1, HF-2 • Bosch Rexroth RE 90220

SUNOCO SUNVIS 600 ASHLESS HYDRAULIC are compatible with most zinc-containing hydraulic oils, however, mixing the two products will lessen the environmental and performance benefits.

TYPICAL PROPERTIES

Product Code	4263	4223	4663	4653	4243	4253
Product	615	622	632	646	668	6100
Viscosity, cSt @ 40 °C	15	22	32	46	68	100
Viscosity, cSt @ 100 °C	3.5	4.8	6.2	7.5	8.9	10.8
Viscosity Index	93	108	100	100	98	96
Flash Point, COC, °C, min.	180	190	200	210	220	240
Pour Point, °C, max.	-55	-50	-50	-42	-37	-25
TOST, D943, hrs.	10,000+	10,000+	10,000+	10,000+	10,000+	5,000+
Demulsibility, mins.	20	20	20	20	20	20
FZG Pass, Load Stage	10	10	10	10	10	10
Biodegradability in 28 days, OECD 301B, %	20-59	20-59	20-59	20-59	20-59	20-59
Dielectric Strength, kV	48	48	40	47	48	48