

Tectyl[®] 5187



Description

TECTYL[®] 5187 is a water-based corrosion preventive designed for application to automotive

underbodies. This compound will dry to a wax-like film.

Laboratory Data

Consistency	Black colored, thixotropic liquid
Film Type	Black colored wax-like film
Non-Volatile Content (by weight)	39%
Non-Volatile Content (by volume)	37%
VOC (lbs/gal minus water)	0.2
Weight/Gallon	8.5
Specific Gravity	1.02
Flash Point	None - Water Base
Shelf Life	90 days (min.)
Removal: Wet Film (1/2HR after application)	Soap and water
Removal: Dry Film	Mineral Spirits
Freeze/Thaw Stability	POOR - DO NOT FREEZE PRODUCT
Dry Time to Touch (25°C,50%RH)	½ to 1 Hour

Application

TECTYL[®] 5187 can be applied using conventional underbody rustproofing equipment. Daubert recommends a 15:1 airless pump or greater that can deliver 800-1200 psi to a .017 to 0.25 reverse-a-clean tip. Tectyl 5187 should be applied at temperatures above 50 °F to allow for proper film formation.

Corrosion Preventive Properties

Parameters of Test

Substrate	Cold Rolled, Elpo, Plastisol, or Topcoated 4X12 Steel Panels
Coating Film Thickness	10 to 12 mils wet, 3 to 4 mils dry
Aging of Panels	72 hours @ 25°C

TEST	RESULTS
Humidity 100% Condensing - 1000 hours	No defects
5% Salt Spray ASTM B-117 - 500 hours	No defects; 1 mm creep back
Gravelometer -20°C, C-SAE-J400	Good or Better rating
Corrosion Cycles, GM 9505P-G - 30 cycles	No defects
Salt Water Immersion, MIL-C-0083933-A(MR)	No defects
Top Coat Cleanability, GM 998-5448	Removable with no staining
Top Coat Compatibility, GM 998-5448	No discoloration
Detergent Wash Test, GM 998-5448	No defects
QUV 500 Hours (Min.)	No defects
QUV/Salt Spray	No defects
High Temperature Flow Resistance, 93°C	No sagging
Water Wash Resistance, 24 Hrs Dry Time	Film remains intact

July 7, 2010:kc

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.



PAGE 2 OF 2

4700 South Central Avenue ■ Chicago, IL 60638 ■ 1-800-688-0459 ■ or 708-496-7350 ■ Fax: 708-496-7367

Visit our web site at www.daubert.com ■ Our e-mail is dauchem@daubert.com

