



PRODUCT INFORMATION

DAUBERT
CHEMICAL COMPANY, INC.

Tectyl® 810



Description

TECTYL® 810 is a water emulsifiable, oil concentrate corrosion preventive compound. The film is thin and

oily. TECTYL® 810 has excellent lubricity for a variety of industrial metalworking.

Laboratory Data

Typical Properties

Flash, COC*, Minimum	325°F
Density, Weight/Gallon @ 77°F (25°C)	7.7 ± 0.2 lbs./gallon
API Gravity @ 60°F (15.6°C)	19.2-21.4
Specific Gravity @ 60°F (15.6°C)	0.92
†Recommended Dry Film Thickness over Metal Profile	0.05 mils
†Theoretical Coverage @ Recommended DFT	31,438 sq. ft./gallon
Non-Volatile % by Weight	99 ± 1
Non-Volatile % by Volume	98 ± 1
Volatile Organic Content (VOC), Maximum	0.23 lbs./gallon
Pour Point	-5°F
†Falex 3500 pound load	Pass

Accelerated Corrosion Tests:

†5% Salt Spray (Hours) ASTM** B-117 @ Recommended DFT (2x4x1/8 in. Polished Steel Panels)	144
†100% Relative Humidity (Hours) ASTM D-1748 @ Recommended DFT (2x4x1/8 in. Polished Steel Panels)	1200
†DIN***50017SK @ 1.25 microns (125 x 200 mm DIN 1623 Panels)	

*COC (Cleveland Open Cup)

**ASTM (American Society for Testing and Materials)

***DIN (Deutsche Industrie Normen)

†Data based upon 10 percent TECTYL 810 in water

Surface Preparation

The maximum performance of TECTYL[®] 810 can be achieved only when the metal surfaces to be protected are clean, dry, and free of rust, oil, and mill scale. Daubert Chemical Company recommends that the metal substrate temperature be 50 - 95°F (10 - 35°C) at the time of product application.

Application

TECTYL[®] 810 is primarily applied in water emulsions in 5 to 25 percent concentrations. Proper concentrations of TECTYL[®] 810 should be evaluated before implementing its use. Consult Daubert Chemical Company for further information. TECTYL[®] 810 may be used in recirculating systems at 40 - 120°F (4 - 49°C). When mixing, always add the oil to the water with the oil and water at 70 - 90°F (21 - 32°C).

Removal

TECTYL[®] 810 can be removed if necessary with TECTYL[®] HPS solventborne thinner, vapor degreasing, or standard hot alkali systems.

Caution

Refer to Daubert's Material Safety Data Sheet for health and safety information.

Note:

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus adversely affecting the performance of this coating as stated in the lab data section. If a product other than Daubert Chemical Company's recommended product is required, written authorization must be obtained from Daubert Chemical Company.

June 18, 2011:co

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

DAUBERT
CHEMICAL COMPANY, INC.

PAGE 2 OF 2

4700 South Central Avenue ■ Chicago, IL 60638 ■ 1-800-688-0459 ■ or 708-496-7350 ■ Fax: 708-496-7367

Visit our web site at www.daubert.com ■ Our e-mail is dauchem@daubert.com

