



Clear Wax

Clear Wax is a low color, translucent rustproofing compound designed to provide a long term protective film for automotive primed and unprimed steel. This product has a thin gel, but low viscosity that allows for film builds on vertical surfaces and for seam penetrations (capillary action) into areas with metal-to-metal overlap. The resulting film is wax-like in nature and will repel water, self-heal and remain flexible at low temperatures. Clear Wax was formulated to pass all the requirements of Honda's Specification titled Test Method on Wax.

PHYSICAL PROPERTIES

TYPICAL VALUES

• Appearance (Liquid)	Translucent color, thixotropic liquid
• Appearance (Film)	Non-tacky, pliable, wax-like translucent film
• Odor:	Mild Petroleum Solvent
• Solvent:	Rule 66 Mineral Spirits
• Specific Gravity:	0.864
• Weight per gallon:	7.2
• Flash Point:	100F. (minimum)
• Viscosity @ 25 C, Brookfield LV, Spindle#3 @ 30 rpm:	1100 cps
• Solids (by weight):	38%
• Wt per gallon of solvent:	6.4
• Solids by volume:	30%
• V.O.C.:	4.5



**UNDER
COATING**
IN A CAN

Clear Wax

Performance Properties

Note: All panels were prepared according to Honda's test method on waxes. Dry film thickness of Clear Wax on 4X12 automotive grade cold rolled steel panels was 1.2 to 2 mils dry for all corrosion tests. Panels were air dried for 24 hours before testing.

Salt Spray, 500 hrs., Scribed:	Pass, no corrosion or degradation of film.
Scrap Cycle Test (3 Cycles):	Pass, no corrosion or degradation of film.
Humidity Test 500 Hrs.:	Pass, no corrosion or degradation of film.
High Temperature Sag Resistance 1 Hr @ 100°C	Pass, no flow of film.
Top Coat Paint Stain 8 Hrs @ 80°C	Pass, no effect on automotive paint.

Undercoating-In-A-Can, Provided exclusively by:

Petroleum Service Company • www.petroleumservicecompany.com • 1 (855) 899-7467





APPLICATION PROCEDURES

Application

Clear Wax can be applied using low pressure airless or air assisted airless equipment using accessory spray wands capable of coating critical areas through existing openings or drilled 1/2" access holes. Contact a UCIAC Sales Representative for recommendation on equipment. The recommended film thickness for Clear Wax is 6 mils wet resulting in a 2 mil dry film. Dry time at this thickness is 4 hours to touch and overnight for full cure. When used as an undercoating, recommended 5 mils dry.

Note

This is a heavy wax-based product and over-sprayed areas can create more of a hazier appearance. This can be remedied by brushing out the heavy areas with a paint brush while still wet. It is recommended that you first apply to a test area to determine the best coverage and visual results you would like to achieve.

Removal

The wet and dry film of Clear Wax can be removed using mineral spirits or a kerosene-soaked rag.

CAUTION:

The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY:

UCIAC warrants all products manufactured by it to be free from defects in material and workmanship. UCIAC MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY UCIAC. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to UCIAC. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL UCIAC BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No UCIAC representative or other person is authorized to change this warranty in any way or to assume for UCIAC any other liability in connection with the sale or use of its products.

Undercoating-In-A-Can, Provided exclusively by:

Petroleum Service Company • www.petroleumservicecompany.com • 1 (855) 899-7467

